

**3M** Science.  
Applied to Life.™



**Prevent leaks.  
Seal it water tight.**

## **3M™ All Weather Flashing Tape 8067**

3M™ All Weather Flashing Tape 8067 is a self adhesive tape that is used to provide a weatherproof seal around openings and penetrations in exterior walls, as well as for sealing joints in rigid air barriers.

# 3M™ All Weather Flashing Tape 8067

## No primers, no staples, no bleeding... No nonsense!

3M™ All Weather Flashing Tape 8067 is engineered to increase productivity while solving the most critical flashing problems. Unique acrylic pressure sensitive adhesive, sticks and stays stuck, to seal around windows, doors and other openings, as well as for sealing joints in rigid air barriers. To prevent moisture intrusion, the thin backing construction effectively conforms and seals around nails and staples with less buildup under siding.

- Fast-convenient application
  - Split-liner for easy and accurate positioning of tape, especially long lengths
  - Bonds to most common building materials without primers and staples even at temperatures as low as -18°C or as high as 49°C
  - No adhesive melting or staining in the summer heat
- High tack to grab fast and tight even on damp surfaces
- Innovative, thin proprietary design reduces aggregate thickness around windows and doors while effectively sealing around nails and staples
- No adverse reaction with most building sealants (preliminary data for synthetic rubber, butyl, polyurethane, silicone and silane terminated hybrids)
- Resists UV exposure for up to 6 months
- BRANZ appraised #775 (2012)
- Passes nail sealability before and after thermal cycling
- Meets AAMA 711-05
- Approved by the International Code Council Division 07. Evaluation ESR-2797

Test Description	Tape Thickness (Backing & Adhesive)	Adhesion to Housewrap*	Adhesion to Polyethylene	Adhesion to OSB	Nail Sealability before and after Thermal Cycling	Adhesion to Anodized Aluminium after 7 days at 80°C	Adhesion to Anodized Aluminium after 7 days in water	Adhesion to Anodized Aluminium after Thermal Cycling	Adhesion to Anodized Aluminium after UV Exposure	Application Temperature Range °C	Service Temperature Range °C
Test Method	ASTM 3652	ASTM D-3330 per AAMA 711-05	ASTM D-3330 per AAMA 711-05	ASTM D-3330 per AAMA 711-05	ASTM E331 as modified per AAMA 711-05 Annex 1	ASTM D3330 after conditioning per AAMA 711-05	ASTM D3330 after conditioning per AAMA 711-05	ASTM D3330 after conditioning per AAMA 711-05	ASTM D3330 after conditioning per AAMA 711-05	ASTM D3330	Tested per AAMA 711-05
Results	0.25mm	55N/100mm	66N/100mm	66N/100mm	Pass	77N/100mm	71N/100mm	82N/100mm	66N/100mm	-18 to 49°C	-40 to 80°C

Note: This technical information and data should be considered representative or typical only and should not be used for specification purposes.  
\* Spun bonded polyethylene



3M™ All Weather Flashing Tape 8067 is available in the following roll sizes:

- 50mm x 22.8m
- 76mm x 22.8m
- 152mm x 22.8m
- 228mm x 22.8m

Additional widths may be available on request.

3M recommends the use of polyurethane or hybrid sealants for a good bond to the flashing tape backing.

To learn more, see our video:

[www.youtube.com/watch?v=zHLgCT\\_E37Y](https://www.youtube.com/watch?v=zHLgCT_E37Y)

Product Use: All statements, technical information and recommendations contained in this document are based on tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose other than those already stated by 3M, and suitable for the user's method of application.

Limitation Of Liability: Except where prohibited by law, 3M and seller will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental, or consequential regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.



**3M Australia Pty Ltd**  
Industrial Adhesives and Tapes Division  
Bldg A, 1 Rivett Road  
North Ryde NSW 2113

Phone 136 136 (Option 2)  
Email [3mindustrialau@mmm.com](mailto:3mindustrialau@mmm.com)  
Web [www.3m.com.au](http://www.3m.com.au)

**3M New Zealand Ltd**  
Industrial Adhesives and Tapes Division  
94 Apollo Drive, Rosedale  
Auckland 0632

Phone 0800 474 787  
Email [3mnz@mmm.com](mailto:3mnz@mmm.com)  
Web [www.stickwith3m.co.nz/flashing](http://www.stickwith3m.co.nz/flashing)

3M is a trademark of 3M Company.  
© 3M 2017. All rights reserved.  
AV011453436